

Polyprop Matt II

200µm

Material Description High quality film with a polypropylene base. This film is tear resistant and has other properties like high durability and no-“yellowing”. Economy product for different applications. Proper light transmission for exact colour expression. Polypropylene is an more environmentally responsible product, Since polypropylene contain only carbon and hydrogen atoms, it does not poison environment after its disposal.

- Qualifications**
- A fine Matt coated finish
 - Polypropylene base material
 - Print side: matt white surface
 - Reverse side: White satin
 - Available in 36", 42"x 30m
 - Core size: 2"



- Details**
- Suitable printing condition: temperature 15-30°C / humidity 30-60%
 - Dye based inks and pigmented inks are compatible
 - Over laminating, the printer material prolong the life of the print
 - Ambient temperature and weather can affect the condition of the product

- Applications**
- Presentation systems (roll ups,, etc...
 - Shop display
 - Backlit applications
 - Exhibitions

Physical Properties	Quality	Polypropylene
	Weight	150g/m ²
	Thickness	2050µm test method: ASTM D645
	Print side	Matt Instant dry coating
	Reverse side	White satin
	L.a.b.	85/1/-7 test method: ANSI T (D50/2°/Abs/No)
	yellowness	30 test method: ASTM D1925
	glossiness	3/5 test method: ASTM 2457

Compatibility

Hewlett packard
Epson
Canon
Oce
And more...

 WB Pigment (UV)
 WB dye

Make your own practical test to be sure it reaches your quality standard.
 For all- and latest information see our Compatibility List.

Printing guidelines Ink restrictions and heater settings have to be set for specific printer ink combinations to obtain the best results.

Colour profiles ATgraphix develops high quality ICC colour profiles for the divers printing media's. We work with specialists who can produce your profile if it's not direct available from our library. Please contact us for the possibilities.

Storage conditions 1 year under normal conditions (10–25°C at a relative humidity of 50 %). Higher humidity and/or temperature can affect the product performance. Always store the media in a dark place.

Environment The media and final prints can be disposed of as polypropylene. Material is suitable for recycling. Please consult local recycle resources.